

Note: "Y" = endurable
"0" = conditionally endurable
"-" = unendurable

Substance	Concentration	Temp.°C	Endurance
Ethanol		40	Y
Formic acid	100%	40	Y
Aqueous ammonia	10%	60	Y
Phenylamine	Concentrated	40	Y
Mixture of gasoline and benzene		20	-
Benzene		20	-
Butane		20	-
Aluminic acid		60	Y
Cyclohexane		20	Y
Cyclohexanol		40	Y
Decahydronaphthalene		60	Y
Diethyl ether		60	Y
Diesel oil		20	-
Acetic acid	100%	20	Y
	10%	20	0
Formalin		40	Y
Ethylene glycol		40	Y
Heptane		60	Y
Caproylhydride		40	Y
Alkaline liquor	10%	60	Y
Mineral chameleon	40%	60	Y
Potassium sulfite	Saturated at 20C	60	Y
Aqua regia	Saturated at 20C	60	Y
Phenol		60	Y
		40	0
Ligroine		20	-
Machine oil		20	Y
Methanol		60	Y
Sodium chloride	10%	20	Y
Sodium bisulfite	10%	60	Y
Sodium hypochlorite	10%	60	Y
Sodium bicarbonate solution	10%	60	Y
	40%	60	Y
Oliver oil		60	Y
Petroleum ether		60	Y
Phosphoric acid	10%	20	Y
	85%	60	Y
Hydrochloric acid	10%	60	Y
	35%	60	Y
Azotic acid	10%	60	Y
Sulfuric acid	10%	60	Y
	96%	60	Y
Terebenthene		60	Y
Methylbenzene		20	Y
Transformer oil		20	Y
Mixed dimethyl benzene		60	-
		20	Y